

TIGFIL 80S-B2

Classification

AWSA/SFA 5. 28 : ER 80S-B2

Approvals

TOYO ER 80S-B2

Identification: AWS classification embossed at one end of the wire.

Characteristics

A GTAW/TIG fille/rod suitable for welding of 1.25% Cr & 0.5% Mo. It deposits notch free weld deposit with excellent mechanical properties. Good X-ray quality welds.

Typical Applications

Specially developed for welding of pipes and tubes of matching composition in power plants, Refineries, Petrochemicals and Fertilizers Plant. Suitable for ASTM A 199 - 76, ASTM A 200 - 75, ASTM A 213 - 76D, ASTM A 335 - Gr. P11, ASTM A 369 - 76, ASTM A 387 Gr. B, DIN 15CrMo3.

Wire Chemistry, wt %

C	Mn	Si	S	P	Mo	Cr	Cu
0.07-0.12	0.40-0.70	0.40-0.70	0.025 max	0.025 max	0.40-0.65	1.20-1.50	0.35 max

Properties of weld metal with 100% Argon gas shielding **Current Condition: DC (-)**

All Weld Mechanical Properties (after SR at 620°C for 1 hour)

UTS MPa	560-670
Yield strength MPa	470-540
Elongation % (L=4xd)	21-27
The chemistry & mechanical properties of the weld metal will vary with the type of shielding gas used.	

Packing Data

Dia (mm)	1.6	2.0	2.5
Length (mm)	1000	1000	1000
Primary Tube (Kg)	5	5	5
No. of Tubes	4	4	4
Secondary Cartons (Kg)	20	20	20

TIGFIL Wires are sealed in polyethylene bags and then packed in primary tubes.

TIGFIL Wires are also available in 5 Kg PSLW spools in 0.8, 1.0 and 1.2 mm sizes for orbital GTAW/TIG welding.

AUTOMIG 80S-B2, in spool form, available for GMAW process, on demand.



WELDERS TO THE NATION SINCE 1951
ADOR WELDING LIMITED

(Formerly Known as Advani-Oerlikon Ltd.)

www.adorwelding.com

